
Feb 2021







Due to the technical limitations of digital cameras and inconsistencies of display monitors, the characteristics and colors of the fabrics seen on your screen may be slightly different than the actual product.

OmegaTEX™ is one of the strongest, all-inclusive screen options on the market. Designed to offer protection from sun, wind, rain, insects, dust, and debris. OmegaTEX™ protects against storm events and has passed certification under the Dade County Projectile Test when used with screening systems NOA labeled and Miami-Dade tested.


**WEAVE CONSTRUCTION: 22 x 13.5** 


\*Custom colors and widths available. Minimum order of 1000 yds. Upcharges may apply. \*\* Available in 28 lyd rolls.

1-800-633-7550 | twitchellcorp.com Twitchell Technical Products, LLC

## Specifications

**REACH Compliant** - Regulated by Registration, Evaluation, Authorization and Restriction of Chemicals. REACH places greater responsibility on industry to manage the risks that chemicals may pose to human health and the environment.







RoHS Compliant - Free of Lead (Pb), Cadmium (Cd), Mercury (Hg), Hexavalent chromium (Hex-Cr), Polybrominated biphenyls (PBB), and Polybrominated diphenyl ethers (PBDE).

Bacteria and Fungal Resistance - Passes ASTM E 2180, ASTM G21. Includes specially formulated antimicrobial.





















## **Technical Data**

**Product Number:** T18KKS | **Roll Length:** Approximately 30 Linear Yards Product Description: A fabric .027" diameter vinyl coated 1500 denier polyester core yarns in warp and .030" diameter vinyl coated 2000 denier Twaron core yarns in fill.


Attribute	ASTM	Warp	Fill	Typical
Construction	D3775-96	22.0 +/- 0.5	13.5 +/- 0.5	
Weight, oz/yd2	D3776-96			19.524
Tensile Strength (grab), lbf	D5034-95	711.3	748.9	
Tensile Strength (strip), lbf	D5035-95	416.7	251.4	
Tear Strength, (Trapezodial), lbf	D1117-97	181.6	285	
Elongation, %	D5035-95	42.8	12.3	
Abrasion Resistances	D3884-92	No exposure to core yarn	No exposure to core yarn	
Weatherability, 1200 hours	G53-96	Trace discoloration	Trace discoloration	
Ball Burst, lbf*	D3787			460+
Bursting Strength, psi*	D3786			1250+
Puncture Resistance, lbf	D4833			364
Porosity Calculation				Open: 9% / Cover: 91%

The above results are a representation of real data from single test samples. Presently no specification is incorporated.


Style	Ts	Rs	As	Tv	Rv	Av	Tuv	O-F	SC 1/8" CI	R-Factor 1/8" CL
Black Profile Angle 0	0.08	0.04	0.88	0.12	0.05	0.83	0.08	0.08	0.18	1.365
Black Profile Angle 45	0.05	0.04	0.91	0.06	0.13	0.81	0.08	0.08	0.16	1.365

DISTRIBUTED OR MANUFACTURED BY:









Black T18KKS002 x 126"

Due to the technical limitations of digital cameras and inconsistencies of display monitors, the characteristics and colors of the fabrics seen on your screen may be slightly different than the actual product.